



FS - Laboratorij za preizkušanje materialov  
**Gradiva - natezni preizkus**



**Datum:** 09. 04. 04 - 13:12  
**Material:** A1Cu6BiPb-sk1  
do: 4,0mm  
lo: 20,0mm  
  
Fm= 3818N  
Rm= 304MPa



**Datum:** 09. 04. 04 - 13:17  
**Material:** C15E4  
do: 4,0mm  
lo: 20,0mm  
  
Fm= 7402N  
Rm= 589MPa