



FS - Laboratorij za preizkušanje materialov
Gradiva - natezni preizkus



Datum: 15. 04. 04 - 10:15
Material: d50-15apr-12
do: 4,0mm
lo: 20,0mm

Fm= 3761N
Rm= 299MPa



Datum: 15. 04. 04 - 10:08
Material: c15-15apr1
do: 4,0mm
lo: 20,0mm

Fm= 7281N
Rm= 579MPa